



B500B - SLOVENIA

STANDARD: STS-09/0066:2014 (TECHNICAL AGREEMENT)

PRODUCT TYPE: REINFORCING STEEL BARS STS-09/ 0066 B500B

DIMENSION: \varnothing mm 8 - 10 - 12 - 14 - 16 - 18 - 20 - 22 - 24 - 25 - 26 - 28 - 30 - 32

CHEMICAL COMPOSITION (%)

	C	S	P	Cu	N	Ceq	It is permitted to exceed the maximum values for carbon by 0,03 % by mass, provided that the carbon equivalent value is decreased by 0,02 % by mass
Cast analysis	0,22	0,050	0,050	0,80	0,012	0,50	
Product analysis	0,24	0,055	0,055	0,85	0,014	0,52	

MECHANICAL PROPERTIES

	CHARACTERISTIC VALUEI		SIGLE VALUE	
	Min	MAX	Min	MAX
UPPER YIELD STRENGTH R_{eH} (MPa)	500	650	485	670
R_m/R_{eH}	1,08	1,30	1,06	
PERCENTAGE TOTAL ELONGATION AT MAXIMUM FORCE A_{gt} (%)	5,0		4,0	


GEOMETRIY

DEVIATION FROM NOMINAL MASS (%)	$\varnothing \leq 8$	$\pm 6,0$
	$\varnothing > 8$	$\pm 4,5$
RELATIVE RIB AREA f_R	$\varnothing = 8 \div 10 \div 12$	$\geq 0,040$
	$\varnothing > 12$	$\geq 0,056$

BEND AND RE-BAND

Angle of bend		
= 180°		
Bend mandrel		
$\varnothing \leq 16$ mm	$\varnothing > 16$ mm	
$3\varnothing$	$6\varnothing$	
Angle of bend	Ageing	Angle of re-bend
= 90°	1 h (-0,+15 min) at 100°C $\pm 10^\circ$ C	$\geq 20^\circ$
Bend mandrel		
$\varnothing \leq 16$ mm	$16 < \varnothing \leq 25$ mm	$\varnothing > 25$ mm
$5\varnothing$	$8\varnothing$	$10\varnothing$

MARKING



QSE

Baryzzi Mario

QSM

Brunori Andrea